Applicant: Pimentel et al. Application No.: Not Yet Known

REMARKS/ARGUMENTS

The Specification, Drawings, and Claims have all been amended to conform the application to US practice. Claim 8 is added herewith.

In view of the foregoing, Applicants respectfully submit that the present application, including the claims, is in condition for allowance and a notice to that effect is respectfully requested.

Respectfully submitted,

João Luiz Pimentel et al.

Stephen B. Schott

Registration No. 51,294

(215) 568-6400

Volpe and Koenig, P.C. United Plaza, Suite 1600 30 South 17th Street Philadelphia, PA 19103

SBS/jf Enclosures

JC14 Rec'd PCT/PTO 22 SEP 2005

[0001]PROCESS OF INERTIZATION (DAMPENING) OF STEEL MAKING SLAG FOR ECONOMICAL REUSE [0002]FIELD OF INVENTION [0003]This invention refers to an economical process in which the steel slag can be reused, through inertization (aeration and hydration). Specifically, this invention refers to an improvement in the steel slag recycling. [0004]BACKGROUND [0005] The steel alloys' manufacturing processes are well known, as well as the inherent residue generation, like mud and slag, of which the steel slag can be evidenced. Its technical application and environmentally adequate solution is the objective of the development of this process. [0006] Collection and storage of the steel slag creates various problems like handling, transportation, loading, unloading and stocking for the huge amounts of this material, each of them with its own structure for environmental protection, especially water contamination. Having in mind the rigorous inspection of environment protection agencies and social and environmental consciousness, metallurgical industries began researches seeking not only to avoid environmental damage due to their residue, as well as promoting the correct technical employment of these materials, and even making some profit through the application in road paving with asphalt coating as a replacement for petroleum compounds.

[0008] The LD steel slag is obtained in the pig iron to steel transformation
process, on LD type converters, in which the oxides formed during the oxygen blow
combine themselves with the dissolved CaO and MgO, creating the slag that is steady
(stable) and distinct from the molten bath.
[0009] The utilization of LD slag in road pavement is well known in many
countries since decades ago, and the problems that may happen in the paving using
this kind of slag are well known too. Being worth of note is the volumetric expansion
caused mainly by the CaO and MgO that are free from the slag, causing ruptures in
the asphalt or concrete covering.
[0010] The term cured steel slag, commonly refers to the slag which is free from
the risk of expanding, once it has been stored for a minimum period of 6 months,
despite some texts affirming that the slag has to be stored for 01 a minimum (one)
year, or even 02 (two) years, to be considered cured. However, the time variable is no
the only responsible factor for the stabilization of the slag. The agents that cause the
stabilization of the slag is water and atmospheric air through hydration and
$\underline{carbonatation}\underline{carbonation}ofthefreeCaOandMgOoxides,transformingthemintostable$
hydrates and carbonates. Due to the hydraulic characteristics of the slag, rainwater,
for instance, that falls on a pile of slag will react with the CaO and SiOa oxides,
forming a film, obstructing, like this, the influx of water in the interior of the pile,
slowing the curing process.
[0011] The difference between the cure conditions of the surface and the interior
of the slag piles is one of the main factors that will result in problems in road paving,
supposing, mistakenly, that the whole material is cured just for the fact of being stored
for a minimum period of 06 months.

Because of this problem, which has become a worldwide matter, some
alternatives to eliminate the volumetric expansion of the steel slag have been
developed, achieving the inertization of the slag.
[0013] The most efficient solutions were identified in Europe and Japan, where
volumetric expansion is reduced to near-zero levels. However, the cost benefit of these
technologies was one of the responsible factors for making its access practically
impossible in emerging economies.
[0014] What follows is a summary of some of the known processes.
[0015] KNOWN PROCESSES
[0016]PROCESS: Increase of the fusible dissolution
[0017] DESCRIPTION: Granulometry reduction
[0018] MOMENT OF ACTUATION: Before generation
[0019] STRONG POINTS: Low Cost
[0020] WEAK POINTS: NIA
[0021] EFFECTIVENESS (Amount of Expansion Reduction): Not defined
[0022]PROCESS: Alteration of the slagging agent
[0023] DESCRIPTION: Utilizing a synthetic material as fusible
[0024] MOMENT OF ACTUATION: Before generation
[0025] STRONG POINTS: Also increases the hydraulic activity of the slag
[0026] WEAK POINTS: Does not change the free MgO ratio
[0027] EFFECTIVENESS (Amount of Expansion Reduction): Low
[0028]PROCESS: Silex and oxygen addition
[0029] DESCRIPTION: Silex and oxygen addition to the liquid slag with a heat
source

[0030] MOMENT OF ACTUATION: After the generation, with the slag in liquid
state
[0031] STRONG POINTS: Reduction in the free CaO and MgO ratios below the 1
% level
[0032] WEAK POINTS: High Cost
[0033] EFFECTIVENESS (Amount of Expansion Reduction): Medium
[0034]PROCESS: Granulation with water
[0035] DESCRIPTION: Abrupt cooling with water
[0036] MOMENT OF ACTUATION: After the generation, with the slag in liquid
state
[0037] STRONG POINTS: Also increases the hydraulic activity of the slag
[0038] WEAK POINTS: Alteration in granulometry; drying needed;
environmental problems
record DDDDGDVDVDGG (A
[0039] EFFECTIVENESS (Amount of Expansion Reduction): High
[0039] EFFECTIVENESS (Amount of Expansion Reduction): High
[0039]EFFECTIVENESS (Amount of Expansion Reduction): High [0040]PROCESS: Dry granulation
[0040]PROCESS: Dry granulation
[0040]PROCESS: Dry granulation [0041] DESCRIPTION: Dry abrupt cooling
[0040]PROCESS: Dry granulation [0041] DESCRIPTION: Dry abrupt cooling [0042] MOMENT OF ACTUATION: After the generation, with the slag in liquid
[0040]PROCESS: Dry granulation [0041] DESCRIPTION: Dry abrupt cooling [0042] MOMENT OF ACTUATION: After the generation, with the slag in liquid state
[0040]PROCESS: Dry granulation [0041] DESCRIPTION: Dry abrupt cooling [0042] MOMENT OF ACTUATION: After the generation, with the slag in liquid state [0043] STRONG POINTS: Also increases the hydraulic activity of the slag;
[0040]PROCESS: Dry granulation [0041] DESCRIPTION: Dry abrupt cooling [0042] MOMENT OF ACTUATION: After the generation, with the slag in liquid state [0043] STRONG POINTS: Also increases the hydraulic activity of the slag; simpler than granulation with water
[0040]PROCESS: Dry granulation [0041] DESCRIPTION: Dry abrupt cooling [0042] MOMENT OF ACTUATION: After the generation, with the slag in liquid state [0043] STRONG POINTS: Also increases the hydraulic activity of the slag; simpler than granulation with water [0044] WEAK POINTS: Alteration in granulometry
[0040]PROCESS: Dry granulation [0041] DESCRIPTION: Dry abrupt cooling [0042] MOMENT OF ACTUATION: After the generation, with the slag in liquid state [0043] STRONG POINTS: Also increases the hydraulic activity of the slag; simpler than granulation with water [0044] WEAK POINTS: Alteration in granulometry

[0048] MOMENT OF ACTUATION: After the generation, with the slag in solid
state
[0049] STRONG POINTS: Low cost and simplicity
[0050] WEAK POINTS: Slow; Lacks a methodological definition, Heterogeneity
[0051] EFFECTIVENESS (Amount of Expansion Reduction): Variable
[0052]PROCESS: Open yard steam cure
[0053] DESCRIPTION: Steam injection in the slag
[0054] MOMENT OF ACTUATION: After the Generation, with the slag in solid
state
[0055] STRONG POINTS: Considerable reduction in free Cao and MgO ratios
[0056] WEAK POINTS: High cost, particularly if there is no steam tubing
available
[0057] EFFECTIVENESS (Amount of Expansion Reduction): High
[0058]PROCESS: SKAP steam cure
[0058]PROCESS: SKAP steam cure [0059] DESCRIPTION: Steam injection in the slag on a sterilizer
[0059] DESCRIPTION: Steam injection in the slag on a sterilizer
[0059] DESCRIPTION: Steam injection in the slag on a sterilizer [0060] MOMENT OF ACTUATION: After the Generation, with the slag in solid
[0059] DESCRIPTION: Steam injection in the slag on a sterilizer [0060] MOMENT OF ACTUATION: After the Generation, with the slag in solid state
[0059] DESCRIPTION: Steam injection in the slag on a sterilizer [0060] MOMENT OF ACTUATION: After the Generation, with the slag in solid state [0061] STRONG POINTS: Considerable reduction in free CaO and MgO ratios
[0059] DESCRIPTION: Steam injection in the slag on a sterilizer [0060] MOMENT OF ACTUATION: After the Generation, with the slag in solid state [0061] STRONG POINTS: Considerable reduction in free CaO and MgO ratios [0062] WEAK POINTS: High cost
[0059] DESCRIPTION: Steam injection in the slag on a sterilizer [0060] MOMENT OF ACTUATION: After the Generation, with the slag in solid state [0061] STRONG POINTS: Considerable reduction in free CaO and MgO ratios [0062] WEAK POINTS: High cost
DESCRIPTION: Steam injection in the slag on a sterilizer [0060] MOMENT OF ACTUATION: After the Generation, with the slag in solid state [0061] STRONG POINTS: Considerable reduction in free CaO and MgO ratios [0062] WEAK POINTS: High cost [0063] EFFECTIVENESS (Amount of Expansion Reduction): Very high
DESCRIPTION: Steam injection in the slag on a sterilizer [0060] MOMENT OF ACTUATION: After the Generation, with the slag in solid state [0061] STRONG POINTS: Considerable reduction in free CaO and MgO ratios [0062] WEAK POINTS: High cost [0063] EFFECTIVENESS (Amount of Expansion Reduction): Very high [0064] SUMMARY
DESCRIPTION: Steam injection in the slag on a sterilizer [0060] MOMENT OF ACTUATION: After the Generation, with the slag in solid state [0061] STRONG POINTS: Considerable reduction in free CaO and MgO ratios [0062] WEAK POINTS: High cost [0063] EFFECTIVENESS (Amount of Expansion Reduction): Very high [0064] SUMMARY [0065] The Economic Reuse of the Steel Slag through its inertization (aeration
DESCRIPTION: Steam injection in the slag on a sterilizer [0060] MOMENT OF ACTUATION: After the Generation, with the slag in solid state [0061] STRONG POINTS: Considerable reduction in free CaO and MgO ratios [0062] WEAK POINTS: High cost [0063] EFFECTIVENESS (Amount of Expansion Reduction): Very high SUMMARY [0065] The Economic Reuse of the Steel Slag through its inertization (aeration and hydratation hydration), is the result of researches and tests on experimental lots of

[0066]	BRIEF DESCRIPTION OF THE DRAWING(S)
[0067]	Figure A is a photograph showing a ruptured asphalt layer used in the
Prior Art.	
[0068]	Figure B is a photograph of an asphalt layer that used the present
process.	
[0069]	Figure C is a table and graph showing an acceptance analysis.
[0070]	<u>DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT(S)</u>
[0071]	To make the process of economical reuse of steel slag through its
inertization	(aeration and hydratation hydration) better visualized, two photographs are
attached to	this report through Figure 01. The first (A), shows a ruptured layer of
asphalt beca	ause of the use of unprocessed slag, and on the second (B) shows an
asphaltic la	yer applied over the steel slag that was inertized through the present
process.	
[0072]	The Economic Reuse of the Steel Slag through its inertization (aeration
and hydratatic	on <u>hydration</u>) begins after the definition of an area to receive the slag, being
prepared th	rough topographical instructions that allow the proposed process to be
carried out.	
[0073]	After the area is defined and adapted, it will be called inertization yard,
	the process of unloading the slag, which will be laid through trucks and,
	th specific equipment, and distributed in homogenous way over the area
	eviously defined thickness is achieved all over the area.
· · · · · · · · · · · · · · · · · · ·	
[0074]	_With the inertization yard prepared, the slag is ready to go through the
	eration, process that starts with the movement of the slag with a leveling
-	

is indicated, as well as specific factors for acceptance analysis of a particular material lot (according to the example below). See Figure C).

[TABLE AND GRAPHS]

[0080] For the residual volumetric expansion verification of the inertized
product, the chosen method is the "PTM-130", that was developed Pennsylvania
Transportation Department (USA) and adapted by the Minas Gerais Highway
Department DER/MG).
[0081] Besides the volumetric expansion test, it is necessary to verify the
granulometry, the density, the ideal humidity and the California Support Index, vital
evaluation characteristics of the aggregates to be used in the execution base and sub-
base for road pavements.
[0082] With the process of Economic Reuse of the Steel Slag through its
inertization (aeration and hydratation hydration), the LD steel slag, that has been
adequately enhanced and submitted to the inertization process accordingly to the
quality control criteria described above, can be used as aggregate in the execution of
road work, as base and sub-base pavement element, as well as aggregate for asphaltic
concrete.

machine, a plough, a bulldozer or any other equipment capable of promoting the aeration of this material through its mixture, causing, subsequently, the acceleration of the earbonatation carbonation of the free magnesium and calcium oxides existing in the slag, increasing the slag's contact with atmospheric air.

After the initial movement of the material laid in this yard, representative [0075]samples of the lot are taken for volumetric expansion level (initial volumetric expansion) analysis. [0076]Simultaneously to the aeration process, the hydratation hydration process is done, through water aspersion with a water truck, or aspersers installed on the inertization yard, arranged in a way so that all the slag is reached, accelerating the hydration reactions of the oxides contained in the slag, especially the free magnesium and calcium oxides, which are the main responsible for the volumetric expansion of the slag. [0077] These procedures are done daily, until the soil laboratory, responsible for the expansion level analysis, decides to halt the wekwork, based on the periodic analysis of the volumetric expansion level of the slag lot being processed. [0078]The water volume to be used during the inertization process will depend on the characteristic of each slag lot submitted to the process, once this characteristic depends on the type of produced steel, as well as other factors.

[0079] The ending of the inertization process of a certain lot of slag follows the control and quality criteria defined by the appropriate road standards, DNER-ES-301197 AND DNER-ES-303197 standards, on which the necessary amount of samples